

Coated Blockout

610gsm 500\*500 28\*28

| Item                  | Data                                  | Unit   | Test Method                  |
|-----------------------|---------------------------------------|--------|------------------------------|
| Fabric                | High tenacity yarns<br>100%PES(1000D) |        | DIN EN ISO2060               |
| Construction          | Weaving 28*28                         | inch   | DIN60001                     |
| Total weight          | 610                                   | g/sq.m | DIN53352 BS3424<br>method5A  |
| Weight of fabric      | 120                                   | g/sq.m | DIN53352 BS3424<br>method5B  |
| Weight of pvc coating | 490                                   | g/sq.m | DIN53352 BS3424<br>method5B  |
| Tensile strength      | Warp: 1800                            | N/5cm  | DIN53354 BS3424<br>method6A  |
|                       | Weft: 1300                            |        |                              |
| Tearing strength      | Warp: 130                             | N      | DIN53356 BS3424<br>method 7A |
|                       | Weft: 100                             |        |                              |
| Adhesion              | 80                                    | N/5cm  | DIN53357 BS3425<br>method9B  |
| Suitable temperature  | -20 -----+70                          | °C     | DIN 53372 BS3424<br>method10 |
| Flame retardancy      |                                       | No     |                              |
| Lacquering            |                                       | No     |                              |

Ink Printability

Eco-Solvent , Solvent , UV , Latex

Note

The indexes above are on average, so there will be ±5% tolerance of actual indexes.