

Laminated Frontlit

440gsm 300*500 18*12

Item	Data	Unit	Test Method
Fabric	High tenacity yarns 100%PES(300D*500D)		DIN EN ISO2060
Construction	Knitting 18*12	inch	DIN60001
Total weight	440	g/sq.m	DIN53352 BS3424 method5A
Weight of fabric	55	g/sq.m	DIN53352 BS3424 method5B
Weight of pvc coating	385	g/sq.m	DIN53352 BS3424 method5B
Tensile strength	Warp: 635	N/5cm	DIN53354 BS3424 method6A
	Weft: 450		
Tearing strength	Warp: 125	N	DIN53356 BS3424 method 7A
	Weft: 110		
Adhesion	60	N/5cm	DIN53357 BS3425 method9B
Suitable temperature	-20 -----+70	°C	DIN 53372 BS3424method10
Flame retardancy		No	
Lacquering		No	

Ink Printability

Eco-Solvent , Solvent , UV , Latex

Note

The indexes above are on average, so there will be ±5% tolerance of actual indexes.