

Laminated Frontlit

510gsm 1000*1000 9*9

| Item | Data | Unit | Test Method |
|-----------------------|---|--------|------------------------------|
| Fabric | High tenacity yarns 100%PES(1000D*1000D) | | DIN EN ISO2060 |
| Construction | Knitting 9*9 | inch | DIN60001 |
| Total weight | 510 | g/sq.m | DIN53352 BS3424 method5A |
| Weight of fabric | 85 | g/sq.m | DIN53352 BS3424 method5B |
| Weight of pvc coating | 425 | g/sq.m | DIN53352 BS3424 method5B |
| Tensile strength | Warp: 1350 | N/5cm | DIN53354 BS3424 method6A |
| | Weft: 1100 | | |
| Tearing strength | Warp: 160 | N | DIN53356 BS3424 method 7A |
| | Weft: 135 | | |
| Adhesion | 60 | N/5cm | DIN53357 BS3425 method9B |
| Suitable temperature | -20 -----+70 | °C | DIN 53372 BS3424 method10 |
| Flame retardancy | | No | |
| Lacquering | | No | |

Ink Printability

Eco-Solvent , Solvent , UV , Latex

Note

The indexes above are on average, so there will be ±5% tolerance of actual indexes.